



# SİMAY KİMYA LTD.ŞTİ

## PLASCOL PC 400

### Features:

<b>Appearance:</b>	white-yellow - granule
<b>Kind of product:</b>	compound of special synthetics, copolymers and modifeid starch
<b>Moisture (at 105 °C):</b>	max. 10%
<b>pH value (10% conc.):</b>	6,5 - 8,5
<b>Viscosity (10%conc., at 85 °C):</b>	50 - 125 Pa.s, 30 rpm, 1. sp, Soif NDJ-8S or 12 – 18 seconds, ford cup 4

### Preparation of The Solution

The required quantity of product is added to cold water. Under stirring the slurry should be heated up till 95 °C and kept for at least 20 minutes at this temperature.

**Desizing** Washed out quickly without enzymes.

### Properties

- Excellent sizing effect
- Transparent and flexible films
- Compatible with other sizing agent
- Good biological degradability

**Storage** Products in their original bags, moisture-free, has a lifetime of 2 years in a dry and well ventilated storage conditions.

**Special Note** The data contained in this safety information and advice should be observed when using the product.